



Shaw Steel Gauge Chart

36615 Vine Street, Willoughby OH 44094
440-946-3331

Carbon Steel Sheets (HR, HRPO, Cold Rolled)

Gauge	Decimal	HR/HRPO Range	Cold Rolled Range
10	.1345	.1265-.1425	.1285-.1405
11	.1196	.1116-.1276	.1136-.1256
12	.1046	.0966-.1126	.0986-.1106
13	.0897	.0827-.0967	.0847-.0947
14	.0747	.0677-.0817	.0697-.0797
15	.0673	.0613-.0733	.0623-.0723
16	.0598	.0538-.0658	.0548-.0648
17	.0538	.0478-.0598	.0498-.0548
18	.0478	.0428-.0528	.0438-.0518
19	.0418		.0378-.0458
20	.0359		.0329-.0389
21	.0329		.0299-.0359

22	.0299	.0269-.0329
23	.0269	.0239-.0299
24	.0239	.0209-.0269
25	.0209	.0179-.0239
26	.0179	.0159-.0199
27	.0154	.0144-.0184
28	.0149	.0129-.0169
29	.0135	.0115-.0155
30	.0120	.0110-.0130

Galvanized Steel Sheets

Gauge	Decimal	Tolerance Range
10	.1382	.1292-.1472
11	.1233	.1143-.1323
12	.1084	.0994-.1174
13	.0934	.0854-.1014
14	.0785	.0705-.0865
15	.0710	.0650-.0770
16	.0635	.0575-.0695
17	.0575	.0525-.0625
18	.0516	.0466-.0566
19	.0456	.0406-.0506
20	.0396	.0356-.0436
21	.0366	.0326-.0406
22	.0336	.0296-.0376
23	.0306	.0266-.0346

24	.0276	.0236-.0316
25	.0247	.0207-.0287
26	.0217	.0187-.0247
27	.0202	.0172-.0232
28	.0187	.0157-.0217
29	.0172	.0142-.0202
30	.0157	.0127-.0187